

DESCRIPTION

Long life TRUCK cast film, for lamination of trucks' canvas

COLORS Transparent gloss

TECHNICAL INFORMATION

FILM	P.V.C. Cast
THICKNESS FILM (WITHOUT ADHESIVE)	80 +/- 5 micron
LINER	Clay coated paper 1 side siliconised
RELEASE	100 +/- 30 cN/20 mm
ADHESIVE	Permanent adhesive extremely high adhesiveness onto plasticized P.V.C.
GRAMMAGE	45 +/- 5 g/m2
PEEL 180° AFTER 24 H ON BANNER PVC AT 20°C (ISTR. OP. N° 7)	min. 400 N/m
SHRINKAGE (48 H AT 70°C ON STEEL)	< 0,2 mm
LIFE *	5 years outdoor (When properly processed, on flat surface and under vertical condition)
APPLICATION TEMPERATURE	Suggested between 10 and 28 °C
TEMPERATURE RESISTANCE	From -50°C to + 90°C adhered to steel no variation
SEAWATER RESISTANCE (ISTR. OP. N° 14)*	Adhered to steel no variation after 100 h at 20°C (Ist. Op. 14)
SHELF LIFE	1 year normal condition (20°C / 50% R.H.) suspended horizontally or vertically upright position in polythene bag (The gloss vinyl might get matt**).

* References made to outdoor durability is based on middle european conditions. Exposure to conditions of high temperature as in southern climatic regions or in high polluted areas or in high altitudes or high UV conditions will reduce the performance levels. All Apa-Print media, is quality controlled to eliminate joints dust and surface imperfections. The values and data given are referred to not printed films and are intended only as a source of information and do not constitute a warranty or a guarantee. It's important that the inks are thoroughly dried before application and before any lamination takes place. Customers must determine the suitability of Apa-Print media with there own printers and inks. APA branded products are manufactured under careful quality control and are warranted against defect in material and workmanship. APA's aggregate responsibility to the purchaser shall in no circumstances exceed the cost of the defective material supplied. No salesman, representative or agent has authority to give any guarantee, warranty or make any representation contrary to these guidelines. **During the storage, the brightness of gloss vinyl could decrease considerably, especially at high temperatures. Cast vinyls could have a further reduction in brightness.